

# DuPont™ Styrofoam™ Brand Cavitymate™ Ultra XPS Foam Insulation

## Durable, High R-Value, Cavity Wall Insulation

### FEATURES/BENEFITS

#### Description

DuPont™ Styrofoam™ Brand Cavitymate™ Ultra Extruded Polystyrene (XPS) Foam Insulation\* is a moisture-resistant, durable and lightweight extruded polystyrene foam board specifically designed for use in wet cavity wall environments. Manufactured with a patented carbon black technology, Styrofoam™ Brand Cavitymate™ Ultra features an R-value of 5.6 per inch (RSI of 0.97 per 25 mm)\*\*, the highest of all extruded polystyrene foam insulation products. Its closed cell structure provides advanced long-term thermal performance and moisture control.

#### Available Sizes

U.S. and Canadian sizes, R-values, and edge treatments can be found in Tables 1 and 2, respectively.

#### Ease of Installation

Styrofoam™ Brand Cavitymate™ Ultra Insulation boards are easy to handle, cut and install. Styrofoam™ Brand Cavitymate™ Ultra can save time and money on the job site.

#### Sustainable Solutions

Styrofoam™ Brand Cavitymate™ Ultra Insulation uses BluEdge™ technology. It is hydrochlorofluorocarbon (HCFC) free with zero ozone depletion potential. Styrofoam™ Brand insulation products produced in North America contain an average of 20% pre-consumer recycled content certified by UL Environment Inc.

**TABLE 1: U.S. Sizes, R-values and Edge Treatments for Styrofoam™ Brand Cavitymate™ Ultra XPS Foam Insulation**

Nominal Board Thickness <sup>(1)</sup> , in.	RSI (R-value) <sup>(2)</sup>	Ultra air barrier wall system Board Size, in.	Standard Board Size, in.	Edge Treatment
2.18	12.0	15 3/4" x 96"	16" x 96"	Square Edge
2.50	14.0	15 3/4" x 96"	16" x 96"	Square Edge
3.00	16.8	15 3/4" x 96"	16" x 96"	Square Edge

<sup>1</sup> Not to be considered sales specifications.

<sup>2</sup> R means resistance to heat flow. The higher the R-value, the greater the insulating power. R-values are expressed in ft<sup>2</sup>·h·°F/Btu. R-value determined by ASTM C518.

**TABLE 2: Canadian Sizes, R-values and Edge Treatments for Styrofoam™ Brand Cavitymate™ Ultra XPS Foam Insulation**

Nominal Board Thickness <sup>(1)</sup> , mm	RSI (R-value)	Ultra air barrier wall system Board Size, mm	Edge Treatment
75	2.90 (16.5)	400 x 2400	Square Edge
91	3.52 (20)	400 x 2400	Square Edge
75	2.90 (16.5)	600 x 2400	Square Edge

<sup>1</sup> Additional thicknesses available. Contact your DuPont representative for more information. Not all thicknesses available in all regions.

<sup>2</sup> RSI or R-value means resistance to heat flow. The higher the RSI or R-value, the greater the insulating power. R-values are expressed in ft<sup>2</sup>·h·°F/Btu. RSI values are expressed in m<sup>2</sup>·C/W. R-value determined by ASTM C518.

\* Styrofoam™ Brand Cavitymate™ Ultra ST-100 (SB) XPS Insulation is a product of DuPont de Nemours.

\*\* Aged R-value (RSI) at 75°F (24°C) mean temp. R means resistance to heat flow. The higher the R-value or RSI, the greater the insulating power. Refer to Table 3 for thermal resistance at other mean temperatures.

## PROPERTIES

DuPont™ Styrofoam™ Brand Cavitymate™ Ultra Extruded Polystyrene (XPS) Foam Insulation exhibits physical properties as indicated in Table 3 when tested as represented. Review all instructions and (Material) Safety Data Sheet ((M)SDS) before use. Please contact DuPont at 1-833-338-7668 when additional guidance is required for writing specifications that include this product.

**TABLE 3: U.S. Physical Properties of Styrofoam™ Brand Cavitymate™ Ultra Extruded Polystyrene Foam Insulation**

Test Method	Property	Typical Value	Units
ASTM C518	Thermal Resistance <sup>(1)</sup> per in.	<u>2.125"</u> <u>2.5"</u> <u>3.0"</u> 12.0   14.0   16.8	ft <sup>2</sup> x h x °F/Btu, R-value, 1 min. @ 75°F mean temp.
ASTM D1621	Compressive Strength <sup>(2)</sup>	25	psi, min.
ASTM C272	Water Absorption	0.1	% by volume, max.
ASTM E96	Water Vapor Permeance	<u>2.125"</u> <u>2.5"</u> <u>3.0"</u> 0.8   0.65   0.50	perm, max.
-	Maximum Use Temperature	165	°F
ASTM D696	Coefficient of Linear Thermal Expansion	3.5 x 10 <sup>-5</sup>	in/in x °F
ASTM C203	Flexural Strength	50	psi, min.
UL 723	Surface Burning Characteristics for both foam core and finished product Flame Spread Smoke Developed	Class A <25 <450	

<sup>1</sup> Values are consistent with the criteria of ASTM C578 and the FTC R-value rule (16 CFR Part 460).

<sup>2</sup> Vertical compressive strength is measured at 10 percent deformation or yield, whichever occurs first. Since Styrofoam™ Brand Extruded Polystyrene Foam Insulations are visco-elastic materials, adequate design safety factors should be used to prevent long-term creep and fatigue deformation. For static loads, 3:1 is suggested. For dynamic loads, 5:1 is suggested. Contact DuPont for design recommendations.

**TABLE 4: Canadian Physical Properties of Styrofoam™ Brand Cavitymate™ Ultra Extruded Polystyrene Foam Insulation**

Property and Test Method	Value
Thermal Resistance per in. (25 mm), ASTM C518, ft <sup>2</sup> ·h·°F/Btu, (m <sup>2</sup> · °C/W), R-value (RSI) <sup>(1)</sup> min. @ 75°F mean temp. @ 40°F mean temp. @ 25°F mean temp.	5.6 (0.97) 6.0 (1.04) 6.3 (1.09)
Compressive Strength <sup>(2)</sup> , ASTM D1621, psi (kPa), min.	25 (170)
Water Absorption, ASTM D2842, % by Volume, max	0.3
Water Vapour Permeance, ASTM E96, perm (ng/Pa·s·m <sup>2</sup> ), max.	1.5 (90)
Maximum Use Temperature, °F (°C)	165 (73.8)
Coefficient of Linear Thermal Expansion, ASTM D696, in/in·°F (mm/m·°C)	3.5 x 10 <sup>-5</sup> 6.3 x 10 <sup>-2</sup>
Flexural Strength, ASTM C203, psi, min.	43.5 (300)
CAN/ULC S102.2 Surface Burning Characteristics for both foam core and finished product <sup>(3)</sup> Flame Spread <sup>(4)</sup> Smoke Developed	<300 <700

<sup>1</sup> Values are consistent with CAN/ULC S7011-17.

<sup>2</sup> Vertical compressive strength is measured at 10 percent deformation or yield, whichever occurs first. Since Styrofoam™ Brand Extruded Polystyrene Foam Insulations are visco-elastic materials, adequate design safety factors should be used to prevent long-term creep and fatigue deformation. For static loads, 3:1 is suggested. For dynamic loads, 5:1 is suggested. Contact DuPont for design recommendations.

<sup>3</sup> Tested per CAN/ULC S102.2. Refer to UL and CCMC listings for details on foam thickness and maximum density evaluated.

<sup>4</sup> These numerical flame-spread and smoke-developed ratings are not intended to reflect hazards presented by this or any other material under actual fire conditions.

---

## TESTING

### Applicable Standards

DuPont™ Styrofoam™ Brand Cavitymate™ Ultra Insulation meets ASTM C578 Type IV – Standard Specification for Rigid Cellular Polystyrene Insulation. Applicable standards include:

- **C518** – Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- **D1621** – Standard Test Method for Compressive Properties of Rigid Cellular Plastics
- **E96** – Standard Test Methods for Water Vapor Transmission of Materials
- **D696** – Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics Between –30°C and 30°C With a Vitreous Silica Dilatometer
- **C203** – Standard Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
- **D2126** – Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
- **D2842** – Standard Test Method for Water Absorption of Rigid Cellular Plastics

### Notice

Styrofoam™ Brand Cavitymate™ Ultra Insulation complies with the following codes:

- Meets IBC/IRC requirements for foam plastic insulation; see ICC-ES ESR 2142
- BOCA-ES RR 21-02
- Underwriters Laboratories, Inc. (UL) Classified, see Classification Certificate D369
- National Building Code of Canada
- CCMC – Evaluation Listing #11420-L

### Warranty

DuPont can provide technical information to help address questions when using **Styrofoam™ Brand Cavitymate™ Ultra**. Technical personnel are available to assist with any insulation project at 1-833-338-7668. Visit [building.dupont.com/warranties](http://building.dupont.com/warranties) for warranty information.

## HANDLING

**WARNING: For Professional Use Only.** Read and follow the entire Safety, Handling, and Storage section and the Safety Data Sheets (SDSs, formerly MSDSs or Material Safety Data Sheets) carefully before use. The information below is designed to protect the user and allow for safe use and handling of DuPont products. Follow all applicable federal, state, local and employer regulations.

### Precautionary Statements

- Since dust would impair the performance of adhesives and finishes, dusty surfaces should be brushed off before these products are applied. A light-colored, opaque protective covering should be used if excessive solar exposure is expected.
- DuPont™ Styrofoam™ Brand Cavitymate™ Ultra Extruded Polystyrene (XPS) Foam Insulation is combustible; protect from high heat sources. A protective barrier or thermal barrier may be required as specified in the appropriate building code. For more information, consult MSDS, call DuPont at 1-833-338-7668 or contact your local building inspector.

- Do not leave Styrofoam™ Brand Cavitymate™ Ultra exposed to direct sunlight for more than 90 days. Consult a DuPont representative if exposure is expected to be longer than 90 days. Prolonged exposure to ultraviolet radiation may cause the surface of Styrofoam™ Brand Cavitymate™ Ultra to become faded and dusty. The surface degradation will have no measurable effect on the insulating value of the plastic foam unless the deterioration is allowed to continue until actual foam thickness is lost.

### Shelf Life and Storage

When stored outdoors, keep insulation boards covered with white plastic film or light-colored tarps or covered to protect from weather and weighted down to prevent boards from being blown around by the wind. Store above standing water.

### Disposal

Dispose of any residual DuPont product, coated debris, or solvent in accordance with applicable federal, state, and local government regulations.

Distributed by:  
**MasonAccess.com**  
(800) 924-6802



**For more information visit us  
at [styrofoam.com](http://styrofoam.com)  
or call 1-833-338-7668**

**NOTICE:** No freedom from any patent owned by DuPont or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries or regions. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY DUPONT. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. The buyer assumes all risks as to the use of the material. Buyer's exclusive remedy or any claim (including without limitations, negligence, strict liability, or tort) shall be limited to the refund of the purchase price of the material. Failure to strictly adhere to any recommended procedures shall release DuPont Specialty Products USA, LLC or its affiliates, of all liability with respect to the materials or the use thereof. The information herein is not intended for use by non-professional designers, applicators or other persons who do not purchase or utilize this product in the normal course of their business.

### DuPont™ Styrofoam™ Brand Extruded Polystyrene Foam Insulation

**CAUTION:** This product is combustible. Protect from high heat sources. A protective barrier or thermal barrier may be required as specified in the appropriate building code. For more information call the DuPont Contact Center at 866-583-2583 or contact your local building inspector. For emergencies contact Chemtrec 800-424-9300, CCN (Contract Number) 7442.

**WARNING:** Rigid foam insulation does not constitute a working walkable surface or qualify as a fall protection product.

Building and/or construction practices unrelated to building materials could greatly affect moisture and the potential for mold formation. No material supplier including DuPont can give assurance that mold will not develop in any specific system.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM, or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2024 DuPont.