


PRODUCT SUBMITTAL

WIRE-BOND

#1004 Type III Anchor



MATERIAL CONFORMANCE

ASTM A1064/A1064M - (Cold drawn steel wire)
 Tensile Strength - 80,000 psi
 Yield Point - 70,000 psi

ACI / ASCE 530 - (Building code requirements for masonry structures)

SHEET METAL - (Carbon Steel) **ASTM A1008 / A1008M**

Mill Galvanized / Zinc Coating: **ASTM A641 / A641M (0.10 Oz per sq ft)**

Hot Dip Galvanized after fabrication / Zinc Coating
ASTM A153 / A153M-B2 (1.50 oz per sq ft)

Stainless Steel **ASTM 580 / ASTM 580M Type 304** (Type 316 available on special order)

Recycled Content:
 Mill Galvanized & Hot Dipped,
 82.8% Post-Consumer
 17% Post Industrial / Pre-Consumer,

Stainless Steel,
 60% Post Consumer
 V O C Content - 0%



SIZES / FINISHES

#1004 Thickness:	14 gauge	12 gauge	
#1100 Triangle :			
Diameter:	3/16"	1/4"	
Length:	3"	4"	5"
	6"	7"	9"
FINISH:	Mill Galvanized	Stainless Steel	
	Hot Dip Galvanized		

WIRE-BOND

www.wirebond.com

Distributed by:
MasonAccess.com
 (800) 924-6802